

AMENDMENT NO. 1 APRIL 2002
TO
IS 7497 : 1985 SPECIFICATION FOR HIGH ABRASION
FURNACE (HAF) CARBON BLACK
(First Revision)

[Page 4, Table 1, Sl No. (i), col 2] — Substitute 'adsorption' for 'absorption'.

(Page 6, clause A-1.1, line 4) — Substitute '(IRB) No. 6' for '(IRB) No. 5'.

(Page 8, clause A-6) — Substitute the following for the existing:

'A-6 PHYSICAL REQUIREMENTS

A-6.1 The maximum difference in physical properties of vulcanizates containing High Abrasion Furnace (HAF) Carbon black as compared to Industry Reference Black (IRB) No. 6 shall be as given in Table 2.

**Table 2 Difference in Physical Properties of Vulcanizates
Containing(HAF)Carbon Black from IRB No. 6**

Cure Conditions	Tensile Strength <i>Min</i> , MPa*	300 Percent Modulus MPa*	Ultimate Elongation Percent, <i>Min</i>
(1)	(2)	(3)	(4)
15 minutes cure at 145°C	-1.2	-0.1 to + 2.9	-80
30 minutes cure at 145°C	-1.0	+0.2 to +3.2	-70

* 1MPa= approx 10.2 kgf/cm².

(PCD 13)