

AMENDMENT NO. 2 APRIL 2003
TO
IS 7497 : 1985 SPECIFICATION FOR HIGH ABRASION
FURNACE (HAF) CARBON BLACK

(First Revision)

[*Page 4, Table 1, Sl No. (i) col 2 (see also Amendment No. 1)*] — Substitute 'Iodine adsorption' for 'Iodine absorption'.

[*Page 6, clause A-1.1, line 4 (see also Amendment No. 1)*] — Substitute '(IRB) No. 7' for '(IRB) No. 6'.

(*Page 7, clause A-4.1, line 1*) — Substitute '30 minutes' for '15 and 30 minutes'.

[*Page 8, clause A-6, line 3 (see also Amendment No. 1)*] — Substitute 'IRB No. 7' for '(IRB) No. 6'.

(*Page 8, Table 2*) — Substitute the following for the existing:

**Table 2 Difference in Physical Properties of Vulcanizates Containing
High Abrasion Furnace (HAF) Carbon Black as Compared with
Industry Reference Black (IRB) No. 7**

(1)	(2)	(3)
Cure Conditions	Tensile Strength Min , MPa*	300 Percent Modulus, MPa*
30 min at 145OC	3.41	-3.05 to + 0.25
*1 MPa = approximately 10.2 kgf/cm ² .		