

AMENDMENT NO. 2 FEBRUARY 2024

TO

IS 7533 : 2017 TEXTILES — POLYAMIDE (NYLON) MONOFILAMENT YARN FOR FISHING — SPECIFICATION (*Second Revision*)

[(*Foreword, second para, a*)] — Substitute the following for the existing:

‘a) Values for yarns suitable for fabrication of fishing nets have been added; and’

[*Page 1, clause 1*] — Substitute the following for the existing:

‘1 SCOPE

This standard prescribes the requirements of polyamide (nylon) monofilament yarn used in hook and line fishing; and fishing nets.

- a) *Type 1* — polyamide monofilament yarns used for hook and line fishing; and
- b) *Type 2* — polyamide monofilament yarns used in the fabrication of fishing net.’

(*Page 2, clause 5.1*) — Substitute the following for the existing:

‘5.1 Polyamide (nylon) monofilament yarn for hook and line fishing; and for fabrication of fishing nets shall conform to the requirements specified in Tables 1 and 2, respectively.’

(*Page 3, Title of Table 2*) — Substitute the following for the existing:

‘**Table 2 Requirements of Polyamide Monofilament Yarn for Fishing Nets**’.

(*Page 3, Table 2, Sl No. 1, 2 and 3*) — Delete.

(*Page 3, clause 5.2*) — Insert the following clause after 5.2:

‘5.3 UV Resistance

If agreed to between the buyer and the seller, the yarn shall be manufactured from UV stabilized polyamide resin. The UV-stabilized yarn shall have at least 65 percent retention of the original breaking strength, when tested after the same has been exposed to UV radiation and accelerated weathering in accordance with the test method given in Annex B. The mean yarn tenacity before and after UV radiation exposure shall be determined as per the test procedure given in IS 5815 (Part 4).’

(*Page 3, clause 6.1*) — Substitute the following for the existing:

‘6.1 The hank or cheeses containing twines shall be marked with the following information:

- a) Name of the material;
- b) Diameter and runnage;
- c) Net weight of the package;
- d) UV stabilized or not;
- e) Month and year of manufacture; and
- f) Manufacturer’s name, initials or trade-mark, if any.’

Price Group 1

(Page 4, Annex A) — Insert the following annex after Annex A:

‘ANNEX B

(Clause 5.3)

UV RESISTANCE TEST

B-1 TEST SPECIMENS

The test specimens for breaking strength shall be cut from the sample as specified in IS 5815 (Part 4).

B-2 TEST CONDITION

The test shall be carried out with fluorescent UV-B (313 nm or its equivalent). The duration of the test shall be 15 00 h (approximately 62 days). The test cycle shall be 8 h at 60 °C ± 3 °C with UV-radiation alternating after 4 h at 50 °C ± 3 °C with condensation. Irradiance level throughout the test shall be maintained at $0.63^{+0.03}_{-0.00}$ W/m².

B-3 TEST PROCEDURE

B-3.1 Determine the original average breaking strength of the yarn as per the test method specified in IS 5815 (Part 4).

B-3.2 Expose the specimens alternately to ultraviolet light alone and to condensation in one respective cycle.

B-3.2.1 The type of fluorescent UV lamp, the timing of the UV exposure and the temperature of condensation shall be as specified in **B-2**.

B-3.3 Determine the average breaking strength of the specimens separately after UV exposure as mentioned **B-3.2.1**

B-3.4 Determine the percent retention of original strength as follows:

$$\text{Percent retention of original breaking strength} = \frac{b}{a} \times 100$$

where

b = average breaking strength after UV exposure as obtained in **B-3.3**; and

a = average breaking strength before UV exposure as obtained in **B-3.1**.

NOTES

1 The UV source is an array of fluorescent lamps (with lamp emission concentrated in the UV range).

2 Condensation is produced by exposing the test surface to a heated, saturated mixture of air and water vapour, while the reverse side of the test specimen is exposed to the cooling influence of ambient room air.’