

AMENDMENT NO. 1 JULY 1980
TO
IS: 7793-1975 SPECIFICATION FOR ALUMINIUM
ALLOYS FOR I. C. ENGINE PISTONS

Alterations

(*Page 3, clause 3.1*) — Substitute the following for the existing clause:

'3.1 The chemical composition of aluminium alloys for pistons shall be as given in Table 1. The physical properties and the values of coefficient of thermal expansion for the alloys are given in the table for guidance only.'

(*Page 4, Table 1*):

a) *Caption* — Substitute the following for the existing caption:

**'TABLE 1 CHEMICAL COMPOSITION AND PHYSICAL PROPERTIES
OF ALUMINIUM ALLOYS FOR PISTONS'**

b) *Col 1 and 2, second entry* — Substitute '4625' and '46258' for '4658' and '49582' respectively.

c) *Foot-note with '†' mark* — Substitute the following for the existing foot-note:

'†Physical properties are attainable after suitable heat treatment of separately cast or forged test bars. The tensile strength attainable on test pieces taken from the crown portion of the piston shall generally be lower by 25 N/mm² than those specified in the table.'

(*Page 5, clause 6.2*) — Substitute the following for the existing clause:

'6.2 Sampling for Tensile and Hardness Tests — At least one separately cast test bar sample may be taken from each supply batch for tensile test and at least one piston shall be selected from each supply batch for hardness test.'

(*Page 5, clause 7.2*) — Substitute the following for the existing clause:

'7.2 Tensile Test — Tensile test may be carried out on a separately cast test bar selected in accordance with 6.2 and tested for tensile strength according to IS : 1816-1961 'Method for tensile test for light metals and their alloys'."

(SMDC 10)