

**AMENDMENT NO. 1 NOVEMBER 1993
TO
IS 7809 (Part 3/Sec 1) : 1986 SPECIFICATION FOR
PRESSURE SENSITIVE ADHESIVE INSULATING
TAPES FOR ELECTRICAL PURPOSES**

PART 3 REQUIREMENTS FOR INDIVIDUAL MATERIALS

**Section 1 Plasticized Polyvinylchloride Tapes with
Non-Thermosetting Adhesive**

(First Revision)

(Page 4, clause 2.1.1, line 2) — Substitute 'F-PVCp/90/0/Tp' for 'F-PVC/90/0/Tp'.

(Page 6, clause 4.6) — Replace the existing clause by the following:

"4.6 Flammability — When tested in accordance with 6 of IS 7809 (Part 2) : 1977, the tapes shall comply with either:

- (a) The requirements of 6.5(a) of IS 7809 (Part 2) : 1977 in which case it shall be designated by addition of 'FR', as indicated

F-PVCp/90/0/Tp/FR
or

- (b) The requirements of 6.5 (b) of IS 7809 (Part 2) : 1977 in which case it shall be designated as usual and with no addition of 'FR',

(Page 6, clause 4.7) — Replace the existing clause by the following:

'4.7 Electrolytic Corrosion — The electrolytic corrosion shall be measured in accordance to either visual test method as specified in 2 of IS 8516 : 1977 or the wire tensile strength method as specified in 3 of IS 8516 : 1977.'

(Page 6, clause 4.8) — Replace the existing clause by the following:

'4.8 Stability to Accelerated Ageing — When testing for behaviour under accelerated ageing conditions by the method described in Appendix A, the layer shall part clearly from the underlayer and shall be tested for conformance to 'Adhesion to Backing' as specified in 4.3 of this standard.'

(Page 6, clause 4.8) — Add the following new clause after 4.8:

'4.9 Insulation Resistance Test — This test is to be performed as per 4 of IS 8516 : 1977 and in conjunction with IS 2259 : 1963. The central value of insulation resistance shall be at least 10^5 M Ω /25mm width after 24 hours exposure at $27 \pm 2^\circ\text{C}$ and 93 ± 2 percent relative humidity.'

(ET 02)

Printed at Simco Printing Press, Delhi