

AMENDMENT NO. 1 SEPTEMBER 2017
TO
IS 7814 : 2005 PHOSPHOR BRONZE SHEET, STRIP AND FOIL

(Second Revision)

(Page 2, Table 2) — Substitute the following for the existing table:

Table 2 Mechanical Properties of Phosphor Bronze Sheet, Strip and Foil
(Clause 8.1)

Grade	Condition	Thickness Up to and Including mm	Tensile Strength, MPa		Elongation Percent on 50 mm G.L. <i>Min</i>	Hardness, HV			
			Up to and Including 450 mm Wide <i>Min</i>	Over 450 mm Wide <i>Min</i>		Up to and Including 450 mm Wide		Over 450 mm Wide	
						<i>Min</i>	<i>Max</i>	<i>Min</i>	<i>Max</i>
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)
I	0	10	295	295	40	—	80	—	80
	HA	10	340	340	30	100	—	100	—
	HB	10	460	400	8	150	—	130	—
	HD	6	540	495	4	180	—	150	—
	HE	6	620	—	—	190	—	—	—
	HS	0.9	—	—	—	200	—	—	—
II	0	10	310	310	45	—	85	—	85
	HA	10	350	350	35	110	—	110	—
	HB	10	490	460	10	160	—	140	—
	HD	6	570	525	4	180	—	160	—
	HE	6	645	—	—	200	—	—	—
	HS	0.9	—	—	—	215	—	—	—
III	O	10	315	315	50	—	90	—	90
	HA	10	385	385	40	115	—	115	—
	HB	10	495	460	12	170	—	150	—
	HD	6	590	540	6	200	—	165	—
	HE	6	650	—	—	215	—	—	—
	HS	0.9	—	—	—	220	—	—	—
	HES	0.6	—	—	—	240	—	—	—
IV	O	10	345	345	50	—	95	—	95
	HA	10	390	390	40	120	—	120	—
	HB	10	500	460	15	170	—	150	—
	HD	6	590	550	8	200	—	170	—
	HE	6	690	—	5	220	—	—	—
	HS	0.9	—	—	—	230	—	—	—
	HES	0.6	—	—	—	240	—	—	—

NOTES

- 1 The mechanical properties exceeding the range of the specified value shall be as agreed upon between the parties concerned with acceptance.
- 2 For 0.5 mm and below strip thickness special load range to be applied for indentation.
- 3 The tensile test shall be applied to material having thickness up to and including 0.20 mm.

(MTD 08)