

**AMENDMENT NO. 1 AUGUST 1991
TO
IS 7861 (Part 1) : 1975 CODE OF PRACTICE FOR
EXTREME WEATHER CONCRETING
PART 1 RECOMMENDED PRACTICE FOR HOT
WEATHER CONCRETING**

(*Page 10, clause 6.2, last line*) — Substitute the following for the existing matter:

'S = ratio of the specific heat of cement and aggregate to that of water.'

(*Page 10, clause 6.3*) — Substitute the following for the existing clause :
'6.3 In practice, the ratio of the specific heat of cement and aggregate to that of water shall be taken as 0.22 and $T_{wa} = T_a$.'

(CED 2)

Printed at Dee Kay Printers, New Delhi-110015, India