

**AMENDMENT NO. 1 JUNE 1991
TO
IS 7861 (Part 2) : 1981 CODE OF PRACTICE FOR
EXTREME WEATHER CONCRETING
PART 2 RECOMMENDED PRACTICE FOR COLD WEATHER
CONCRETING**

(*Page 11, clause 6.2, last line*) — Substitute the following for the existing
ratio

‘ S = ratio of the specific heat of cement and aggregate to that of water.’

(*Page 11, clause 6.3*) — Substitute the following for the existing clause:

‘ 6.3 In practice the ratio of the specific heat of cement and aggregate to that of
water shall be taken as 0.22 and $T_a = T_{we}$ ’

(CED 2)

Printed at Dee Kay Printers, New Delhi, India