

**AMENDMENT NO. 1 JANUARY 1995
TO
IS 7887 : 1992 MILD STEEL WIRE ROD FOR GENERAL
ENGINEERING PURPOSES — SPECIFICATION**

(First Revision)

(Page 1, Table 1, Note 4) — Substitute the following for the existing Note:

‘4 Any other chemistry may be mutually agreed between the manufacturer and the purchaser.’

(Page 1, Table 1) — Add the following new Note 5 at the end:

‘5 Microalloying may be allowed subject to mutual agreement between the purchaser and the supplier. Microalloying elements like Nb, V or Ti, when used individually or in combination, the total content shall not exceed 0.20 percent.’

(Page 2, Table 2) — Substitute the following for the existing table:

Table 2 Permissible Variation for Product Analysis of Carbon Steel
(Clause 6.2)

Constituent	Limit, or Maximum Specified Range, Percent	Variation Over Specified Maximum or Under the Minimum Limits, Percent
(1)	(2)	Max (3)
Carbon	Up to and including 0.25	0.02
	Over 0.25	0.03
Manganese		0.03
Phosphorus		0.005
Sulphur		0.005
Silicon		0.03

NOTES

1 Variations shall not be applicable both over and under the specified limits in several determinations in a heat.

2 Product analysis shall not apply to rimming quality steel

(Page 2, clause 9) — Add the following new clause 10 after clause 9 and renumber the subsequent clauses:

‘10 Physical properties of the product can also be provided by mutual agreement between the manufacturer and the purchaser.’

(MTD 4)