



TO

IS:8036-1976 SPECIFICATION FOR MILD STEEL
TRANSFORMER COOLING TUBES

Alterations

(Page 4, clause 4.1) - Substitute the following
for the existing clause:

'4.1 The tubes shall be manufactured from mild steel
made by any approved process.

4.1.1 The steel shall have not more than 0.060
percent each of sulphur and phosphorus respectively.

4.1.2 The analysis of steel shall be carried out
either by the method specified in IS:228* and its
relevant parts or any other established instrumental/
chemical method. In case of dispute the procedure
given in IS:228* and its relevant parts shall be
referee method. However, where the method is not
given in IS:228* and its relevant parts, the referee
method shall be as agreed to between the purchaser
and the manufacturer.'

(Page 4, foot-notes with '*' and '+' marks) -
Substitute the following foot-note for the existing
foot-notes:

'*Methods for chemical analysis of steels
(issued in several parts).'

(SMDC 22)