

TO

IS:8119-1976 SPECIFICATION FOR COPPER BRAZED
STEEL TUBINGAlterations

(Page 5, clause 4.1) - Substitute the following for the existing clause:

'4.1 The steel when analyzed shall conform to the following requirements:

<i>Element</i>	<i>Percent, Max</i>
Carbon	0.10
Manganese	0.50
Phosphorus	0.035
Sulphur	0.035

4.1.1 The analysis of steel shall be carried out either by the method specified in IS:228* and its relevant parts or any other established instrumental/chemical method. In case of dispute the procedure given in IS:228* and its relevant parts shall be referee method. However, where the method is not given in IS:228* and its relevant parts, the referee method shall be agreed to between the purchaser and the manufacturer.'

(Page 5, foot-note with '*' mark) - Substitute the following for the existing foot-note:

'*Methods for chemical analysis of steels (issued in several parts).'

(SMDC 22)