

**AMENDMENT NO. 1 APRIL 2003
TO
IS 8134 : 1996 INTERMEDIATE SUPER ABRASION
FURNACE (ISAF) CARBON BLACK
— SPECIFICATION**

(Second Revision)

(Title, cover page 1 and page 1) — Substitute '(ISAF) N220' for '(ISAF)' and wherever appears.

(Page 1, clause 4.4, line 4) — Substitute 'IRB No. 7' for 'IRB No. 6'.

(Page 2, clause A-1, lines 5 and 6) — Substitute 'Industry Reference Black No. 7' for 'Industry Reference Black No. 6'.

(Page 3, clause A-2) — Substitute 'Carbon black (ISAF) N220' for 'Carbon black (ISAF)'.

(Page 3, clause A-4, line 1) — Substitute '30 minutes' for '15 and 30 minutes'.

(Page 3, clause A-6, line 3) — Substitute 'IRB No. 7' for 'IRB No. 6'.

(Page 3, Table 2) — Substitute the following for the existing:

**Table 2 Difference in Physical Properties of Vulcanizates Containing
ISAF Carbon Black IRB No. 7**

Sl No.	Grade	Cure Condition	Tensile Strength, Min (MPa*)	300 Percent Modulus (MPa*)
(1)	(2)	(3)	(4)	(5)
i)	ISAF-HM (N 220)	30 min at 145°C	-3.1	-3.35 to -0.95
ii)	ISAF-LM (N 231)	30 min at 145°C	-2.3	-5.35 to -2.95
iii)	ISAF-LS (N 219)	30 min at 145°C	-1.9	-6.65 to -4.25

*1 MPa = approximately 10.2 kgf/cm².

(PCD 13)

Reprography Unit, BIS, New Delhi, India