

**AMENDMENT NO. 1 MARCH 2003
TO
IS 8135 : 1996 FAST EXTRUSION FURNACE (FEF)
CARBON BLACK—SPECIFICATION**

(Second Revision)

(Title) — Substitute '[(FEF)N550]' for '(FEF)'.

(Page 2, clause 3.4, line 4) — Substitute 'No. 7' for 'No. 6'.

(Page 2, clause 4.1, line 4) — Substitute 'sight' for 'sight'

(Page 2, clause A-2) — Substitute 'IS 3399 : 1993' for 'IS 3399 : 1973'.

(Page 2, clause A-2) — Substitute 'Carbon black [(FEF)N550]' for 'Carbon black (FEF)'

(Page 3, clause A-4.1, line 1) — Substitute '30 minutes' for '15 to 30 minutes'

(Page 3, clause A-6, line 3) — Substitute 'IRB No. 7' for 'IRB No. 6'.

(Page 3, Table 2) — Substitute the following for the existing:

**Table 2 Difference in Physical Properties of Vulcanisates Containing
FEF Carbon Black as Compared to IRB No. 7**

Cure Conditions	Tensile Strength, Min, MPa*	300 Percent Modulus MPa*
(1)	(2)	(3)
30 min at 145°C	- 5.71	- 2.95 to + 0.05

*1 MPa = approximately 10.2 kgf/cm²

(PCD 13)