

AMENDMENT NO. 1 JUNE 1990
TO
IS 12020 (Part 1) : 1987 SPECIFICATION FOR
POLYPROPYLENE FILTER CLOTH

PART 1 FILTER CLOTH FROM SPUN
POLYPROPYLENE YARN

[This Amendment is being issued to include five additional varieties of polypropylene filter cloth made from spun polypropylene yarn, which have wider acceptance by the users.]

(Page 3, clause 1.1) — Substitute 'eleven varieties' for 'six varieties'.

(Page 4, Table 1) — Substitute the table given on page 2 for the existing table:

**TABLE 1 REQUIREMENTS OF POLYPROPYLENE FILTER CLOTH
MADE FROM SPUN YARN**
(Clause 3.1)

VARIETY NUMBER	ENDS/ dm	PICKS/ dm	MASS	BREAKING STRENGTH ON 5×20 cm STRIP, Min		THICK- NESS	AIR PERME- ABILITY	DIMENSIONAL CHANGES ON WASHING IN BOILING WATER	WEAVE
				Warp	Weft				
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)
			g/m ²	N	N	mm	m ² /cm ² /s		
1	200	135	200	1 100	800	0·60	15		2/2 Twill
2	225	170	265	1 400	1 150	0·70	8		2/2 Twill
3	175	110	380	2 700	1 325	1·10	22		2/2 Twill
4	300	150	410	2 550	1 275	1·10	2·5		2/2 Twill
5	235	105	420	3 075	1 225	1·35	3·5	± 2 per- cent in both direc- tions	2/2 Twill
6	355	130	420	3 375	1 200	1·10	7·5		2/2 Oxford Twill
7	220	100	450	2 975	1 325	1·20	3·0		2/2 Twill
8	265	120	510	3 650	1 700	1·20	2·5		2/2 Oxford Twill
9	380	125	580	3 525	1 375	1·30	2·5		2/2 Twill
10	270	110	600	3 225	2 000	1·45	4·0		2/2 Twill
11	210	90	670	4 800	2 100	1·50	4·5		2/2 Oxford Twill
Tolerance	±2·5 per- cent	±5 per- cent	+5 -2·5 per- cent	—	—	±0·05	±1·5	—	—
Me- thod of test	IS 1963 : 1981*	IS 1964 : 1970†	IS 1969 : 1985‡			IS 7702 : 1975§	IS 11056 : 1984	IS 1299 : 1984¶	Visual

NOTE — 1 N = 0·102 kgf approximately.

*Methods for determination of threads per unit length in woven fabrics (second revision).

†Methods for determination of weight per square metre and weight per linear metre of fabrics (first revision).

‡Methods for determination of breaking load and elongation of woven textile fabrics (second revision).

§Method for determination of thickness of woven and knitted fabrics.

||Method for determination of air permeability of fabrics.

¶Method for determination of dimensional changes on washing of fabrics woven from rayon and synthetic fibres (second revision).

(TXD 24)