

**AMENDMENT NO. 2 AUGUST 2002
TO
IS 12120 : 1987 CODE OF PRACTICE FOR
PRESERVATION OF PLYWOOD AND OTHER PANEL
PRODUCTS**

[*Page 5, clause 3.1(b), lines 2 and 3 (see also Amendment No. 1)*] —
Substitute 'trichlorophenol, gamma - BHC (lindane) and chloropyrifos'
for 'pentachlorophenol, benzene hexachloride and p, p'-dichlorodiphenyl -
trichloroethane (DDT)'.

[*Page 5, clause 3.1(c)*] — Substitute the following for the existing:

'c) Type 3 (*Water Soluble, Non-fixed Type*) — Boric acid, borax and
sodium pentachlorophenate.'

(*Page 6, Table 1, Sl No. 2*) — Substitute the following for the existing:

'a) Copper and zinc naphthenates, b) Copper and zinc abielates, c) Trichlorophenol, d) gamma-
benzene hexachloride (lindane), and e) Chloropyrifos'

(*Page 10, clause 5.5*) — Substitute the following for the existing clause:

'5.5 Glue Line Poisoning

For the treatment of plywood meant for use in interior dry locations only, toxins
could be added in glue against powder post beetles (borers) during glue mixing
stage as follows, thus making the treatment procedure very simple:

- a) For amino resins — 2% level boric acid or boric acid — borax at 1:1
level, and
- b) For phenolic resins — 1% level chloropyrifos or 1% lindane.'

(CED 20)