

AMENDMENT NO. 3 NOVEMBER 2009
TO
IS 12120 : 1987 CODE OF PRACTICE FOR PRESERVATION OF PLYWOOD
AND
OTHER PANEL PRODUCTS

[Page 10, clause 5.5 (see also Amendment No. 2)] — Substitute the following for the existing:

‘5.5 For treatment of plywood, toxins could be added in glue during glue mixing stage. For phenolic resins, chlorinated hydrocarbons or any organic chlorophosphate compound shall be added in appropriate doses to glue mix (0.5 percent concentration of chlorophyrifos containing active ingredient of 205 g/m³ in 100 kg of liquid phenol with 50 percent solids content), which shall make the plywood resistant to insects. For amino resins, 2 percent level boric acid or boric acid-borax at 1:1 level shall be added to glue mix for plywood for interior applications.

NOTE — For resistance to other pests, finished plywood shall be treated with Acid-Copper-Chrome or Copper-Chrome-Arsenic or Copper-Chrome-Boron preservatives.’

