

AMENDMENT NO. 2 OCTOBER 2025
TO
IS 6721 : 2023 SANDAL AND SLIPPERS — SPECIFICATION
(First Revision)

[Page 1, clause 5, (see also Amendment no. 1)] — Substitute the following for the existing:

‘5 CATEGORY AND TYPE

The sandals and slippers shall be of the following two categories based on their usage:

- a) For kids (Standard English sizes for infants and children as per IS 1638 up to 220 mm last length); and
- b) For adults (All other standard English sizes as per IS 1638 above 220 mm last length).

NOTE — This categorization is only for the purpose of differentiation between adults and kids and not for the purpose of defining sizes.’

[Page 1, Table 1, Sl No. (xii), col (2), (see also Amendment no. 1)] — Substitute ‘Abrasion resistance⁸’ for ‘Abrasion resistance’.

[Page 1, Table 1, Notes, (see also Amendment no. 1)] — Insert the following at the end:

⁸ Cellular, density less than 0.90g/cm³; and Solid, density more than 0.90 g/cm³.’

[Page 1, Table 1, Sl No. (xiv), col (3), col (4), col (5), (see also Amendment no. 1)] — Substitute ‘Category 1 and Category 2’ for ‘Category I and Category II’.

[Page 2, clause 8.2, (see also Amendment no. 1)] — Substitute the following for the existing:

‘8.2 Insole Covering

The insole covering if present shall conform to the requirements as specified in Table 3.’

(Page 2, clause 8.5) — ‘Delete’.

[Page 5, clause 8.6 (see also Amendment no. 1)] — ‘Delete the clause and the subclauses 8.6.1 and 8.6.2.’

(Page 7, B-3.2, line 2) — Substitute ‘25.5 mm ± 0.5 mm × 25.5 mm ± 0.5 mm’ for ‘25.5 mm ± 0.5 mm × 25 mm ± 0.5 mm square.’

(Page 7, B-3.3, para 1) — Substitute the following for the existing:

‘The carriage moves in a simple harmonic reciprocating motion with a stroke length of 75 mm ± 2 mm at a speed of 30 cycles/min ± 5 cycles/min along the length of the table.’

(Page 7, B-5.3, line 4) — Substitute ‘as TA_1 and TA_2 ’ for ‘ $TA_1 - TA_2$ ’.

(Page 7, B-5.4) — Substitute the following for the existing:

‘B-5.4 Calculate the combined thickness of steel plate and adhesive as:

$$CT_1 = TA_1 - TS_1, CT_2 = TA_2 - TS_2$$

(Page 7, B-6.2) — Substitute the following for the existing:

‘B-6.2 Targeted thickness as: $TT_1 = CT_1 + 0.5$ mm, $TT_2 = CT_2 + 0.5$ mm.’

Price Group 1

Amendment No. 2 to IS 6721 : 2023

(Page 7, **B-6.3**, line 6) — Substitute the following for the existing:

‘thickness gauge at the centre of each test specimen’.

(Page 7, **B-7.1**) — Substitute the following for the existing:

‘B-7.1 Abrasion Rate

$$\text{Sample 1, mm/kcs} = \frac{(TA_1 - FT_1) \times 1\,000}{NC_1}$$

$$\text{Sample 2, mm/kcs} = \frac{(TA_2 - FT_2) \times 1\,000}{NC_2}$$

where

TA_1 and TA_2 = original thickness of the specimen assembly, in mm;

FT_1 and FT_2 = final thickness of the specimen assembly, in mm; and

NC_1 and NC_2 = No. cycles abrasion cycles corresponding to the thickness of FT_1 and FT_2 .