

AMENDMENT NO. 2 JANUARY 1987

TO

**IS:6745-1972 METHODS FOR DETERMINATION OF MASS
OF ZINC COATING ON ZINC COATED IRON AND STEEL
ARTICLES**

(Page 8, clause 5.2.3, last sentence) - Delete
and incorporate the following Note thereunder:

'Note - The time required for stripping
will vary with the coating thickness and
generally should not exceed 1 minute. The
time of 1 minute maximum is to ensure that no
dissolution of iron takes place.'

(SMDC 28)