

AMENDMENT NO. 4 OCTOBER 1996
TO
IS 6745 : 1972 METHODS FOR DETERMINATION OF
MASS OF ZINC COATING ON ZINC COATED IRON AND
STEEL ARTICLES

(*Page 5, clause 3.2.2*) — Insert the following note at the end of the clause:

‘**NOTE** — The wire shall also include the formed wires as per 3.2 of IS 3975 : 1988.’

(*Page 7, clause 5.2.2.1*) — Substitute the following for the existing:

‘5.2.2.1 Calculation

$$M = \frac{M_1 - M_2}{M_2} \times K$$

where

M = mass of zinc coating in g/m^2 of surface,

M_1 = mass of the original test piece in g,

M_2 = mass of the stripped test piece in g, and

The value of the constant K for different sections shall be as under:

<i>Type of Wire</i>	<i>Dimension(s)</i>				<i>Constant</i>
Round	All Sizes				$d \times 1965$
	A	B	C	R	
Formed*	4.0	3.4	0.8	10	2 571
	6.1	5.3	1.4	27.5	4 383

*For further details of the dimensions refer 3.2 of IS 3975 : 1988.’

(MTD 20)