

AMENDMENT NO. 1 SEPTEMBER 2026
TO
IS 6911 : 2026 STAINLESS STEEL PLATE, SHEET AND STRIP — SPECIFICATION
(Third Revision)

[Page 5, Table 1, SI No. (a)(15), (d)(13), (d)(17) and (d)(85)] — Substitute the following for the existing:

SI No.	Grade Designation	Numerical Symbol ISS	C	Si	Mn	Ni	Cr	Mo	S	P	N	Cu	Other
	Letter Symbol (see IS 1762(Part 1))												
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)
15)	X01Cr15Nb	429Nb	0.020	1.00	1.00	—	14.00 to 16.00	—	0.015	0.025	0.02	—	Nb : 0.20 to 0.60
13)	X11Cr8Ni6Mn6N	202S1	0.070 to 0.150	0.50 to 1.00	5.00 to 7.50	6.50 to 8.50	17.50 to 19.50	—	0.015	0.030	0.20 to 0.30	—	—
17)	X05Cr17Mn6Cu2Ni4N	204Cu3	0.080	1.00	5.50 to 7.50	3.50 to 5.50	17.00 to 18.00	—	0.030	0.045	0.10 to 0.25	1.50 to 3.50	—
85)	X02Cr21Ni25Mo5CuNb	8700	0.040	1.00	2.00	24.00 to 26.00	19.00 to 23.00	4.30 to 5.00	0.030	0.040	—	0.50	Nb : 8 × C to 0.40

Price Group 1

Amendment No. 1 to IS 6911 : 2026

[Page 37, Table 4, column numbers] — Substitute the following for the existing:

SI No.	Grade Designation		Hardness, <i>Max</i>			Yield Strength <i>Min</i> , MPa 0.2 Percent Proof Stress	Tensile Strength <i>Min</i> , MPa	Elongation Percent <i>Min</i> 50 mm	Bend Test <i>Dma</i>
	Letter Symbol [see IS 1762 (Part 1)]	Numerical Symbol ISS	Brinell HBS/HBW	Rockwell HRB	Vickers Load (1 kg to 30 kg)				
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)

[Page 37, Table 4, SI No. (i)(10), (i)(15), (i)(19), (i)(20), (i)(32), (i)(39), (i)(40), (iv)(1) and (v)(10)] — Substitute the following for the existing:

SI No.	Grade Designation		Hardness, <i>Max</i>			Yield Strength <i>Min</i> , MPa 0.2 Percent Proof Stress	Tensile Strength <i>Min</i> , MPa	Elongation Percent <i>Min</i> 50 mm	Bend Test <i>Dma</i>
	Letter Symbol [see IS 1762 (Part 1)]	Numerical Symbol ISS	Brinell HBS/HBW	Rockwell HRB	Vickers Load (1 kg to 30 kg)				
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)
10	X02Cr13Nb	410S1	162	80	165	205	380	22	a*
15	X01Cr15Nb	429Nb	183	89	187	210	380 to 560	25	a*
19	X06Cr17Mo1	434	183	89	187	240	450	22	a*
20	X06Cr17Mo1Nb	436	183	89	187	240	450	22	a*
32	X01Cr20CuNb	445	165	83	167	205	427	22	a*
39	X01Cr11Ni1	350	—	—	—	350	450	20	2a*
40	X01Cr11Ni1Mn1	450	—	—	—	450	550	18	2.5a*
1	X10Cr17Mn6Ni4N	201	241	100	248	260	515	40	Not required
10	X02Cr25Ni6Mo3WN	2506	293	32 ^A	303	450	620	18	Not required

(MTD 16)

Publication, BIS, New Delhi