

## AMENDMENT NO. 5 JULY 2024

### TO

### IS 6911 : 2017 STAINLESS STEEL PLATE, SHEET AND STRIP — SPECIFICATION

( *Second Revision* )

(Page 1, clause 2) — Insert the following reference at appropriate place:

| <i>IS No.</i>   | <i>Title</i>                                                                                                                                  |
|-----------------|-----------------------------------------------------------------------------------------------------------------------------------------------|
| IS 14650 : 2023 | Unalloyed and alloyed steel ingot and semi-finished products for re-rolling purposes — Specification ( <i>first revision</i> ) <sup>1</sup> . |

(Page 2, clause 5.2) — Insert the following new clause after 5.2:

‘5.3 Steels used for manufacturing the product covered in the standard shall conform to the requirements of IS 14650.’

[Page 3, Table 1, SI No. (iii) (73) (*see also Amendment No. 1, 2 and 3*)] — Insert the following new rows after SI No. 73:

|     |                                 |    |      |     |           |                         |           |   |       |      |           |         |   |
|-----|---------------------------------|----|------|-----|-----------|-------------------------|-----------|---|-------|------|-----------|---------|---|
| 74) | X06Cr15Mn10Cu2NiN <sup>3)</sup> | N5 | 0.12 | 1.0 | 9.5-11.5  | 0.45-0.95               | 14.0-16.5 | — | 0.030 | 0.10 | 0.10-0.25 | 1.5-2.5 | — |
| 75) | X06Cr14Mn10Cu1NiN <sup>3)</sup> | N6 | 0.12 | 1.0 | 9.25-11.5 | 0.25-0.95               | 13.5-16.0 | — | 0.030 | 0.10 | 0.10-0.25 | 1.0-2.0 | — |
| 76) | X07Cr14Mn10CuNiN <sup>3)</sup>  | N7 | 0.14 | 1.0 | 9.0-11.5  | 0.20-0.95 <sup>2)</sup> | 13.5-16.0 | — | 0.030 | 0.10 | 0.10-0.25 | 0.4-0.8 | — |

[Page 3, Table 1, footnote (*see Amendment No. 2*)] — Insert the following new footnote after 1).

<sup>2)</sup> Stainless steel may be supplied with Ni content 0.20-1.25, if agreed to between the manufacturer and the purchaser.

<sup>3)</sup> Stainless steel grades are generally used for manufacturing welded tubing where appearance is needed.<sup>2</sup>

[Page 6, Table 3, SI No. (iii) (73) (*see also Amendment No. 1, 2 and 3*)] — Insert the following new rows after SI No. 73:

|     |                   |    |    |             |     |   |   |   |   |
|-----|-------------------|----|----|-------------|-----|---|---|---|---|
| 74) | X06Cr15Mn10Cu2NiN | N5 | SA | 950 to 1120 | w,a | — | — | — | — |
| 75) | X06Cr14Mn10Cu1NiN | N6 | SA | 950 to 1120 | w,a | — | — | — | — |
| 76) | X07Cr14Mn10CuNiN  | N7 | SA | 950 to 1120 | w,a | — | — | — | — |

[Page 8, Table 4, SI No. (iii) (73) (*see also Amendment No. 1, 2 and 3*)] — Insert the following new rows after SI No. 73:

|     |                   |    |     |     |     |     |     |    |              |
|-----|-------------------|----|-----|-----|-----|-----|-----|----|--------------|
| 74) | X06Cr15Mn10Cu2NiN | N5 | 241 | 100 | 248 | 350 | 700 | 40 | Not required |
| 75) | X06Cr14Mn10Cu1NiN | N6 | 241 | 100 | 248 | 375 | 750 | 40 | Not required |
| 76) | X07Cr14Mn10CuNiN  | N7 | 241 | 100 | 248 | 400 | 800 | 30 | Not required |

**Price Group 1**

**Amendment No. 5 to IS 6911 : 2017**

[Page 8, Table 4, Note (see Amendment No. 1 and 2)] — Substitute the following for the existing:

‘NOTES

- 1 Tensile test not required for thickness less than 0.3mm.
- 2 During the tensile testing for grades N5, N6 and N7, in case fracture takes place outside the gauge length, re-testing shall be done for the cases in which specified minimum elongation is not achieved.’

(Page 10, clause **19.2**) — Substitute the following for the existing:

**‘19.2 BIS Certification Marking**

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product(s) may be marked with the Standard Mark.’

(Page 11, clause **19.3**) — Delete.

(Page 11, clause **19.3.1**) — Delete.