

AMENDMENT NO. 1 NOVEMBER 1980
TO
IS:7011-1973 SPECIFICATION FOR BACK-SILVERED
MIRRORS USED IN INSTRUMENT INDUSTRY

Alteration

(Page 4, clause 3.1.1) - Substitute the following
for the existing clause:

'3.1.1 A suitable treatment may be given to improve
adhesion of the silver layer. One of the recommended
compositions of the solution for the treatment of mirror
blanks for this purpose is given below:

Stannous chloride	10 g
Hydrochloric acid	40 ml
Water	1 l

NOTE - This solution sensitizes the glass surface to
receive a mirror type film. It is equally important
to carefully wash off all traces of the solution
before metal surface is precipitated.'