

AMENDMENT NO. 3 JULY 2025
TO
IS 11652 : 2017 TEXTILES — HIGH DENSITY POLYETHYLENE (HDPE)/
POLYPROPYLENE (PP) WOVEN SACKS FOR PACKAGING OF 50 KG
CEMENT — SPECIFICATION
(Third Revision)

[Page 1, clause **4.2**, second sentence (see also Amendment No. 1)] — Substitute the following for the existing:

‘The woven fabric shall be of mesh 10×10 per inches and 79 g/m^2 mass (with a tolerance of ± 3 percent on mass).’

(Page 3, Table 1, Note) — Substitute the following for the existing:

‘NOTE — The buyer and the seller may agree to dimensions other than those specified above. However, the fabric specification as specified in **4.2** and tolerances as specified above shall apply. The mass of the sack, for both non-gusseted or gusseted sack, as specified above is of unprinted sack. The mass of the printed ink on sack will depends on the artwork and shall be as agreed to between the buyer and the seller. The mass of the sack with dimensions other than those specified in Table 1 shall be calculated by the method given in Annex E which is for guidance only.’

(Page 6, clause **C-3.1**) — Substitute the following for the existing:

‘**C-3.1** Drop test shall be carried out using suitable sack drop mechanism. Each sack shall be dropped from a height of 1.8 m for the test requirements as specified below:

- a) Height of drop = 1.8 m, (two time for face side and two times for back side); and
- b) Height of drop = 1.8 m (one time for left edge and one time for right edge).’

(Page 6, clause **C-3.2**) — Insert the following at the end:

‘**C-3.3** Three sack (as test specimens) shall be tested by following the procedure as laid down in **C-3.1** for conformity of each sample. All three sack, when dropped, shall conform to the criteria as specified in **C-4**.’