

AMENDMENT NO. 3 DECEMBER 2007
TO
IS 11722 : 1986 SPECIFICATION FOR THIN WALLED
FLEXIBLE QUICK COUPLING PIPES

(Page 3, Foreword, clause 0.2) — Substitute 'IS 1239 (Part 1) : 2004*' for 'IS : 1239 (Part 1)-1979*'.
'

(Page 3, Foreword, footnote marked *) — Substitute the following for the existing:

'Steel tubes, tubulars and other wrought steel fittings — Specification : Part 1 Steel tubes (*sixth revision*).'

(Page 4, Foreword, clause 0.2.1) — Delete.

(Page 4, clause 2.1, read with Amendment No. 2) — Substitute the following for the existing:

'The pipes shall be manufactured from the steel conforming to 'O' grade of IS 513 : 1994† for sizes up to 150 mm. Sizes above 150 mm shall be manufactured from steel conforming to IS 10748 : 2004**.'

(Page 4, clause 3.1) — Substitute 'IS 1387 : 1993‡' for 'IS : 1387-1967‡'.

(Page 4, footnote marked †) — Substitute '(fourth revision)' for '(second revision)'.
'

(Page 4, footnote marked ‡) — Substitute '(second revision)' for '(first revision)'.
'

(Page 4, footnotes) — Add '**Hot rolled steel strip for welded tubes and pipes — Specification (*second revision*)' at the end.

(Page 5, clause 6.1, Table 1, read with Amendment No. 2) — Substitute the following for the existing table:

Amend No. 3 to IS 11722 : 1986

*(Page 7, footnote marked *)* — Substitute the following for the existing:

‘Metallic materials – Tube-flattening test (*second revision*).’

(Page 7, footnote marked †) — Substitute the following for the existing:

‘Metallic materials — Tensile testing at ambient temperature (*third revision*).’

(Page 8, clause 17.2) — Substitute the following for the existing clause:

‘17.2 BIS Certification Marking

Each pipe may also be marked with the Standard Mark.

17.2.1 The use of Standard Mark is governed by the provisions of the Bureau of Indian Standards Act, 1986 and the Rules and regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers, may be obtained from the Bureau of Indian Standards.’

(MTD 19)

Amend No. 3 to IS 11722 : 1986

Table 1 Sizes for Thin Walled Quick Coupling Pipes

Outside Diameter mm	Wall Thickness, mm	
	Type A*	Type B†
25.4	—	1.40
31.8	—	1.40
38.1	—	1.40
50.8	1.00	1.60
63.5	—	1.60
76.2	1.00	1.60
101.6	1.00	1.60
127.0	1.25	1.60
152.4	1.40	1.60
203.2	—	2.0
254.0	—	2.60
304.8	—	3.10

*Pressure activated couplers.

†Mechanically clamped couplers.

(Page 6, clause 9.1) — Substitute 'IS 4736 : 1986*' for 'IS : 4736-1968*'.
(Page 6, clause 10.2) — Substitute 'IS 5382 : 1985†' for 'IS : 5382-1969†'.

(Page 6, Table 2, read with Amendment No. 2) — Insert the following at the appropriate place:

'Outside Diameter	Volume per Minute
63.5 mm	8 ml'

(Page 6, footnote marked *) — Add '(first revision)' at the end.

(Page 6, footnote marked †) — Add '(first revision)' at the end.

(Page 7, clause 13.1) — Substitute 'IS 2328 : 2005/ISO 8492 : 1998*' for 'IS : 2328-1983*'.
(Page 7, clause 13.2) — Substitute 'IS 1608 : 2005/ISO 6892 : 1998†' for 'IS : 1894-1972†'.