

**AMENDMENT NO. 1 OCTOBER 2008
TO
IS 11838 : 1986 RECOMMENDATIONS FOR
MEASUREMENT OF QUALITY
CHARACTERISTICS OF GUDGEON PINS**

(Page 1, clause 3.1.1) — Substitute the following for the existing:

'3.1.1 The outer diameter d_1 shall be measured after soaking the gudgeon pin at $20 \pm 1^\circ\text{C}$ until it reaches the temperature.'

(Page 1, clause 3.1.3, first sentence) — Substitute the following for the existing:

'3.1.3 Gudgeon pin diameter may be checked by a suitable arrangement, with a mechanical comparator having a ruby point or Precision Measuring Microscope of least count $0.5 \mu\text{m}/1 \mu\text{m}$ ($0.5 \mu\text{m}$ is more accurate).'

(Page 4, clause 3.9) — Substitute the following for the existing:

'3.9 *Surface Roughness of Outer Diameter and Inner Diameter and Side Faces* — Shall be tested according to IS 3073 : 1967 'Assessment of surface roughness' with roughness checking stylus instrument. At least three readings to be measured along lengthwise on the circumference for assessment.'

(TED 2)