

AMENDMENT NO. 1 JULY 1990
TO
IS : 11842 - 1986 SPECIFICATION FOR PVC/PLASTIC
HYGIENIC BELTING

(Page 1, Table 1) — Substitute the following for the existing table:

Table 1 Widths and Tolerances

(Clause 3.2)

Width (mm)	Tolerance	Total Variation in Any One Belt
50	± 5 mm	5 mm
75		
100		
125		
150		
175		
200		
225		
250		
300		
400	± 1 percent of belt width	1 percent of belt width
500		
600		
650		
750		
800		
900		
1 000		
1 200		
1 400		
1 600		
1 800		
2 000		

NOTE — The tolerance for width other than given in this table shall be that applicable to the next higher standard width.

(Page 2, clause 5.4.1) — Substitute the following for the existing clause:

'5.4.1 Thickness — Unless agreed between the purchaser and the supplier, the thickness of the top cover will range from 0.1 to 1.0 mm. The value of the cover thickness shall not fall below the specified thickness by more than 0.1 mm when measured as described in Appendix A. The bottom cover will normally be either bare, frictioned or with a skim cover.'

(Page 2, clause 5.4.2) — Substitute the following for the existing clause:

'5.4.2 Unless the design precludes the provision of the edge, as in cut edge belting, the edges shall be suitably protected by means of a distinct layer of PVC compound.'

(Page 3, Table 2) — Substitute the following for the existing table:

Table 2 Full Thickness Breaking Strength (Clause 6.1.1)		
Type	Full Thickness Breaking Strength in kN/m Width, Min	
	Longitudinal Direction	Transverse Direction
90	90	Not specified
95	95	Not specified
110	110	Not specified
115	115	Not specified
120	120	Not specified
125	125	Not specified
130	130	Not specified
135	135	Not specified
140	140	Not specified
160	160	63
180	180	71
200	200	80
224	224	90
250	250	100
280	280	112
315	315	125
355	355	140
400	400	160
450	450	Not specified
500	500	Not specified
560	560	Not specified

NOTE — The plastic hygienic belting of strength range given in this table can be had normally with 2 ply to 4 ply constructions.

(LMD 09)