

**AMENDMENT NO. 1 MARCH 2001  
TO  
IS 4859 : 1968 SPECIFICATION FOR HIGH  
STRENGTH AIRCRAFT PLYWOOD**

*( Page 11, clause 4.16 )* — Substitute the following for the existing:

**'4.16 Treatment of Boards — Boards shall be treated with either trichlorophenol dissolved in light organic solvent or sodium pentachlorophenate dissolved in water to a retention level of 8 kg/m<sup>3</sup> or 6 kg/m<sup>3</sup> respectively.'**

( CED 20 )

---

Reprography Unit, BIS, New Delhi, India