

AMENDMENT NO. 1 DECEMBER 2015
TO
IS 4873 (PART 1) : 2008 METHODS OF LABORATORY
TESTING OF WOOD PRESERVATIVES AGAINST FUNGI
AND BORERS (POWDER POST BEETLES)

PART 1 DETERMINATION OF THRESHOLD VALUES OF WOOD
PRESERVATIVES AGAINST FUNGI

(Second Revision)

(Page 2, clause 2.7.1.1) — Substitute the following for the existing clause:

‘2.7.1.1 For conifers

- a) *Neolentinus lepideus* (Fr.) Redhead & Ginns particularly tolerant to creosote or mixture containing creosotes;
- b) *Oligoporus placentus* (Fr.) Gilb. & Ryv. particularly tolerant to copper and zinc compounds; and
- c) *Gloeophyllum striatum* (Fr.) Murr.’

(Page 2, clause 2.7.1.2) — Substitute the following for the existing clause:

‘2.7.1.2 For non-conifers

- a) *Trametes versicolor* (L) Lloyd or *Pycnoporus sanguineus* (L.) Murr.; and
- b) *Gloeophyllum trabeum* (Pers.:Fr.) Murr. or *Gloeophyllum striatum* (Fr.) Murr.

NOTE — Some strains of *Gloeophyllum trabeum* are highly resistant to arsenic but susceptible to copper.’