

AMENDMENT NO. 3 JUNE 2024
TO
IS 4923 : 2017 HOLLOW STEEL SECTIONS FOR STRUCTURAL USE —
SPECIFICATION
(Third Revision)

(Page 1, clause 2, see also Amendment No. 2) — Substitute the following for the existing:

‘2 REFERENCES

The standards given below contain provisions, which through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreement based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards:

<i>IS No.</i>	<i>Title</i>
IS 228 (Relevant parts)	Methods of chemical analysis of steels
IS 1387 : 1993	General requirements for the supply of metallurgical materials (<i>second revision</i>)
IS 1608 (Part 1) : 2022/ ISO 6892-1 : 2019	Metallic materials — Tensile testing: Part 1 Method of test at room temperature (<i>fifth revision</i>)
IS 2062 : 2011	Hot rolled medium and high tensile structural steel — Specification (<i>seventh revision</i>)
IS 2633 : 1986	Method for testing uniformity of coating on zinc coated articles (<i>second revision</i>)
IS 4736 : 1986	Specification for hot-dip zinc coatings on mild steel tubes (<i>first revision</i>)
IS 6745 : 1972	Methods for determination of mass of zinc coating on zinc coated iron and steel articles
IS 10748 : 2004	Hot rolled steel strip for welded tubes and pipes — Specification (<i>second revision</i>)’.

(Page 2, clause 7.1, see also Amendment No. 2) — Substitute the following for the existing:

‘The seamless hollow steel sections shall be manufactured from steel made by any process at the discretion of the manufacturer which shall show not more than 0.040 percent of sulphur and 0.040 percent of phosphorus. The welded hollow sections shall be manufactured from hot rolled steel strips conforming to IS 2062/IS 10748.’

(Page 4, clause 11.1, see also Amendment No. 2) — Substitute the following for the existing:

‘Hollow steel sections may be varnished, painted, oiled, or galvanized as per agreement between the purchaser and the manufacturer. In the case of galvanizing, the mass of the coating shall be tested as per IS 6745. The requirement of mass of zinc coating shall be as per IS 4736.

NOTE — Mass of zinc coating shall not be less than 360 g/m² when tested on two specimens taken from opposite ends of the tube selected for testing.’

[Page 5, Table 3, Sl No. (v) and (vi), see also Amendment No. 2] — Substitute the following for the existing:

Sl No.	Grade	Yield Strength <i>Min, MPa</i>	Tensile Strength <i>Min, MPa</i>	Elongation Percent on Gauge Length $5.65\sqrt{A}$, <i>Min</i> or Test Piece of Gauge Length 50 mm and Sample Width of 12.5 mm, <i>Min</i>
(1)	(2)	(3)	(4)	(5)
v)	YSt 420	420	500	10
vi)	YSt 460	460	530	10

Amendment No. 3 to IS 4923 : 2017

[Page 6, Table 4, SI No. (v) and (vi), see also Amendment No. 2] — Substitute the following for the existing:

SI No.	Grade	Yield Strength Min, MPa	Tensile Strength Min, MPa	Elongation Percent on Gauge Length $5.65\sqrt{A}$, Min or Test Piece of Gauge Length 50 mm and Sample Width of 12.5 mm, Min	
				Under 25.4 mm*	Over 25.4 mm*
(1)	(2)	(3)	(4)	(5)	(6)
v)	YSt 420	420	500	8	10
vi)	YSt 460	460	530	8	10

(Page 10 and Page 11, Table 2, see also Amendment No. 2) — Substitute the weight of the following sizes for the existing. All other values in the whole table remains same :

Designation/Size mm (1)	Weight kg/m (5)
120 × 60 × 5.0	12.84
127 × 50 × 3.0	7.87
127 × 50 × 3.6	9.34
150 × 100 × 4.0	14.88
150 × 100 × 5.0	18.34
150 × 100 × 6.0	21.69
150 × 100 × 6.3	22.68
150 × 100 × 8.0	28.10
150 × 100 × 10	34.09
150 × 100 × 12	39.67
150 × 100 × 12.5	41.00
260 × 180 × 12	75.47

(Page 15, Annex B, see also Amendment No. 2) — Delete.