

AMENDMENT NO. 1 MAY 2018
TO
IS 4984 : 2016 POLYETHYLENE PIPES FOR
WATER SUPPLY — SPECIFICATION

(Fifth Revision)

(Page 2, clause 3.15, last sentence) — Delete the word ‘potable’.

[Page 3, clause 5.3, Sl No. (e)] — Insert ‘.’ at the end.

(Page 4, clause 6.1) — Substitute the following for the existing clause:

‘6.1 Pipes shall be designated according to the grade of material (*see 6.1.1*) followed by pressure rating (PN) (*see 6.1.4*), nominal outside diameter (*see 6.1.3*) and standard dimension ratio (SDR) (*see 6.1.2*). For example PE 80, PN 5, DN 200, SDR 26 indicates pipe pertaining to material grade PE 80 and pressure rating 5, nominal outside diameter 200 mm and wall thickness corresponding to SDR 26.’

(Page 6, Table 4) — Substitute ‘5.3’ for ‘5.9’ for e_{Min} value for 110 mm nominal outside diameter (d_n) and SDR 21.

(Page 6, Table 4) — Substitute ‘6.0’ for ‘6.6’ for e_{Max} value for 110 mm nominal outside diameter (d_n) and SDR 21.

(Page 7, clause 8.6, line 1) — Delete the word ‘composite’.

(Page 8, clause 9.1.5, see also Amendments to Tables 7 and 8) — Substitute the following for the existing clause:

‘9.1.5 At the end of the validity period (normally one year for internal pressure creep rupture test at 27°C for 100 h and internal pressure creep rupture test for joints at 80 °C for 48 h, and two years for all other type tests) or earlier as may be necessary, the testing authority may call for fresh samples for type-test for the purpose of type approval.’

Price Group 2

Amendment No. 1 to IS 4984 : 2016

[Page 8, Table 7, Sl No. (v), see also Amendment to Table 8] — Insert the following as Sl No. (vi) and renumber the subsequent Sl Nos.:

Sl No.	Description of Test	Sample Size	Requirement Clause
(1)	(2)	(3)	(4)
vi)	Internal pressure creep rupture test (hydrostatic resistance test) for joints at 80 °C for 48 h	3	8.1.2

[Page 9, Table 8, Sl No. (x)] — Delete the entry.

(Page 9, clause **9.2.3.3**, line 2) — Substitute ‘col 4’ for ‘col 3’.

(Page 9, clause **9.2.3.3**, line 9) — Substitute ‘col 6’ for ‘col 5’.

(Page 9, clause **9.2.3.3**, line 13) — Substitute ‘col 7’ for ‘col 6’.

(Page 9, clause **9.2.3.3**, line 16) — Substitute ‘col 6 and col 7’ for ‘col 5 and 6’.

(Page 9, clause **9.2.3.3**, line 17) — Substitute ‘col 4’ for ‘col 3’.

(Page 9, clause **9.2.3.3**, line 22) — Substitute ‘col 6’ for ‘col 5’.

(Page 9, clause **9.2.3.3**, last sentence) — Substitute the following for the existing:

‘In case, the sample size is equal to or less than the lot size, 100 percent inspection shall be done for these tests and all the samples from the lot which pass these tests shall be tested for other acceptance tests.’

(Page 9, clause **9.2.4**, line 3) — Substitute ‘Table 8’ for ‘Table 7’.

(Page 10, Table 10 A, Title) — Substitute ‘Table 10’ for ‘Table 10 A’.

[Page 10, clause **10.1.1(f)**] — Substitute ‘Lot number/Batch number’ for ‘Lot No./Batch No.’.

Amendment No. 1 to IS 4984 : 2016

[(Page 10, clause **10.1.1**] — Insert the following new clause at the end:

‘10.1.1.1 The lot number/batch number shall include the details of production in the following manner:

Year	Month	Day	Machine No.	Shift
XXXX	XX	XX	XXX	XXX

(Page 11, clause **A-1**, line 7) — Insert ‘in bar,’ at the end of the explanation given for *PN*.

(Page 11, clause **A-1**, first para) — Insert the following sentence as a new para after the explanation given for ‘SDR’:

‘The nominal pressure (*PN*) for various material class and different SDRs has been calculated using the above equation and is given in the informal table below.’

(Page 11, clause **A-1**) — Delete the heading ‘Table 11’, and substitute the following for the existing table:

<i>Standard Dimension Ratio (SDR) Used in Wall Thickness Chart (Table 5) at 27 °C</i>				
<i>Sl</i>	<i>SDR</i>	<i>Nominal Pressure for Material Class, in Bar</i>		
<i>No.</i>		<i>PE 63</i>	<i>PE 80</i>	<i>PE 100</i>
(1)	(2)	(3)	(4)	(5)
i)	41	2.0	2.5	3.0
ii)	33	2.5	3.2	4.0
iii)	26	3.2	4.0	5.0
iv)	21	4.0	5.0	6.0
v)	17	5.0	6.0	8.0
vi)	13.6	6.0	8.0	10.0
vii)	11	8.0	10.0	12.5
viii)	9	-	12.5	16.0
ix)	7.4	-	16.0	20.0
x)	6	-	20.0	—

Amendment No. 1 to IS 4984 : 2016

[Page 16, clause **G-3.1.1(b)**] — Substitute ‘ $e \geq 25$ mm’ for ‘ $e > 25$ mm’.

(Page 17, Fig. 3, Title) — Substitute ‘ $\geq$ ’ for ‘ $\leq$ ’.

[Page 18, Table 12, Sl No. (iv)] — Substitute ‘ $d_n \geq 315$ ’ for ‘ $315 \leq d_n < 110$ ’ in col 2.

[Page 20, Table 16, Sl No. (iv)] — Substitute ‘ $d_n \geq 450$ ’ for ‘ $d_n \leq 450$ ’ in col 2.

(Page 22, clause **H-6**) — Substitute the following for the existing formula:

$$E = \frac{L_1 - L_0}{L_0} \times 100$$