

AMENDMENT NO. 1 MARCH 2008
TO
IS 6419 : 1996 WELDING RODS AND BARE
ELECTRODES FOR GAS SHIELDED ARC
WELDING OF STRUCTURAL STEELS —
SPECIFICATION

(First Revision)

(Page 1, clause 5, Table 1) — Substitute '0.05 mm' for '0.07 mm' for Tolerances on minus side for 2.0 mm and 5.0 mm nominal dia.

(Page 5, clause 14.1, second and third sentences) — Substitute 'The chemical analysis shall be made for all sizes' for 'The chemical analysis shall be made using either 1.2 mm or 1.6 mm diameter.....shall be taken for chemical analysis.'

(Page 6, clause 14.3.3.1) — Add the following new clause:

'14.3.3.2 Retest — If the results of any test fail to meet the requirements, that test shall be repeated twice. The results of both retests shall meet the requirements. Specimen for retest may be taken from the original test assembly or from one or two new test assemblies. For chemical analysis, retest need be only for those elements that failed to meet their requirements. If the results of one or both retests fail to meet the requirements, the material under test shall be considered as not meeting the requirements of this specification for that classification.'

(MTD 11)

Reprography Unit, BIS, New Delhi, India