

AMENDMENT NO. 1 JUNE 1975
TO
IS:6472-1971 GENERAL REQUIREMENTS FOR
TINTED OPHTHALMIC GLASS

Addendum

(Page 5, clause 4.6) - Substitute the following for the existing clause:

4.6 'The tinted ophthalmic glass shall be well annealed such that the residual strain is minimum and symmetrically distributed. The retardation due to birefringence in blanks caused by strain shall not exceed 50 nm/cm for glass diameter up to 60 mm of single vision vane and 80 nm/cm for larger size piece of glass.'

(EDC 36)

Reprography Unit, BIS, New Delhi, India