



AMENDMENT NO. 1 JANUARY 1983

TO

IS:6504-1979 METHOD FOR QUANTITATIVE CHEMICAL ANALYSIS
OF TERNARY MIXTURES OF VISCOSE RAYON,
COTTON AND PROTEIN FIBRES

(First Revision)

[This amendment is being carried out mainly to align the procedure given in this standard with the procedure given in IS:1889(Part IV)-1979 Method for quantitative chemical analysis of binary mixtures of regenerated cellulose fibres and cotton: Part IV Sulphuric acid method (*first revision*)].

Alteration

(Page 6, clause 7.3) .. Substitute the following for the existing clause:

'7.3 Dissolution of Viscose Rayon - Transfer the residue as obtained in 7.2 to flask containing 100 ml sulphuric acid (60 percent) at room temperature and stir vigorously to break up the sample completely at the first instant and then shake thoroughly, preferably with a mechanical shaker for 30 minutes. Transfer the contents of the flask to a weighed sintered glass crucible, wash the residue remaining in the flask, using a little more sulphuric acid solution and transfer the contents to the crucible. Then wash the residue twice with a small quantity of dilute sulphuric acid solution followed by distilled water. Then wash the residue with dilute ammonia solution and finally wash the residue thoroughly with water. After each washing drain the crucible with the aid of suction. Dry the residue to a constant mass in an oven at $105 \pm 3^{\circ}\text{C}$, cool and weigh.'



Addendum

(Page 8, clause 9.1(b)(iii)] - Add the following new item after the existing clause:

c) Number of specimens tested.'

(TDC 5)