

**AMENDMENT NO. 4 MAY 2004
TO
IS 6452 : 1989 HIGH ALUMINA CEMENT FOR
STRUCTURAL USE — SPECIFICATION**

(First Revision)

(*Page 1, clause 4.4*) — Insert the following new clause after **4.4**:

‘4.4.1 If cement exhibits false set, the ratio of final penetration measured after 5 min of completion of mixing period to the initial penetration measured exactly after 20 s of completion of mixing period, expressed as percent, shall be less than 50 when tested by the method described in IS 4031 (Part 14) : 1989. In the event of cement exhibiting false set, the initial and final setting time of cement when tested by the method described in IS 4031(Part 5) : 1988 after breaking the false set, shall conform to **4.4**.’

(*Page 2, Annex A*) — Insert the following at the appropriate place:

‘IS 4031 (Part 14) : 1989 Methods of physical test for hydraulic cement : Part 14 Determination of false set’

(CED 2)