

AMENDMENT NO. 1 JULY 2003
TO
IS 653 : 1992 LINOLEUM SHEETS AND TILES —
SPECIFICATION
(Third Revision)

(Page 1, clause 3.2) — Substitute the following for the existing clause:

‘3.2 The type of hessian used for backing is dependent on the type of linoleum, method of manufacture and the machine used for manufacture. It is mandatory on the part of the manufacturer to select correct type of hessian so as to produce linoleum which conform to the requirements stipulated in the present standards.’

(Page 1, clauses 3.3 and 3.3.1) — Delete.

(Page 1, clause 4.2) — Substitute the following for the existing clause:

‘4.2 Linoleum other than plain, shall be designated as in laid linoleum. They are composed of different colours extending from the wearing surface to the backing at random to form a variegated surface.’

(Page 1, clause 5.1.1, line 3) — Substitute ‘5.0’ for ‘5.5’.

(Page 1, clause 5.2) — Substitute the following for the existing:

‘5.2 Thickness

The standard overall thickness of linoleum sheet and tiles shall be 4.5 mm, 3.2 mm, 2.5 mm and 2.0 mm.’

(Page 1, clause 6.2) — Delete.

[Page 3, Table 1, Sl No. (viii)] — Substitute the following for the existing:

viii)	Water absorption	For Thickness	Water Absorption,
		mm	Percent, Max
		4.5	5.5
		3.2	6.5
		2.5	9.0
		2.0	10.0

[Page 3, Table 1, Sl No. (ix)] — Delete.

Amend No. 1 to IS 653 : 1992

[*Page 3, Table 1, Sl No. (x)*]—Substitute 'ix' for 'x' and '8' for '9'.

(*Page 4, List of Referred Indian Standards*) —Delete IS 2818 (Part 2):1991 and its title.

(CED 5)