

AMENDMENT NO. 2 JANUARY 2005
TO
IS 709 : 1974 SPECIFICATION FOR MEDIUM
STRENGTH AIRCRAFT PLYWOOD
(First Revision)

(Page 7, clauses 5, 5.1, 5.1.1 and 5.2) — Substitute the following for the existing clauses:

5 DIMENSIONS AND TOLERANCES

5.1 The dimensions of plywood panels shall be as follows:

1 800 mm × 1 200 mm	1 800 mm × 900 mm
1 500 mm × 1 200 mm	1 500 mm × 900 mm
1 200 mm × 1 200 mm	1 200 mm × 900 mm

5.2 Thickness

The thickness shall be 1.0 mm, 1.5 mm, 2.0 mm, 2.5 mm, 3.0 mm, 3.5 mm, 4.0 mm, 4.5 mm, 5.0 mm, 6.0 mm, 7.0 mm, 8.0 mm, 9.0 mm and 10.0 mm.

NOTE — Any other dimensions (length, width and thickness) as agreed to between the manufacturer and the purchaser may also be used.

5.3 Tolerances

Tolerances on the nominal sizes of finished boards shall be as given below:

<i>Dimension</i>	<i>Tolerance</i>
Length	+ 6 - 0 mm
Width	+ 3 - 0 mm
Thickness:	
i) Less than 6 mm	±10 percent
ii) 6 mm and above	± 5 percent
Edge straightness	2 mm per 1 000 mm or 0.2 percent

Amend No. 2 to IS 709 : 1974

Squareness 2 mm per 1 000 mm
or 0.2 percent

NOTE — Edge straightness and squareness shall be tested as per Annex A.

(Page 8, clause 5.3) — Renumber '5.3' as '5.4'.

(Page 9, clause 7.1.5) — Add the following new clause after 7.1.5.3:

7.1.6 Static Bending Strength — Three test specimens taken in each direction from the sample of plywood, when tested in accordance with IS 1734 (Part 11) : 1983 shall have an average and a minimum individual Modulus of Elasticity and Modulus of Rupture not less than the values specified in Table 1.

Table 1 Average and Minimum Individual Values of Modulus of Elasticity (MOE) and Modulus of Rupture (MOR)

Direction	MOE (N/mm ²)		MOR (N/mm ²)	
	Average	Min. Ind.	Average	Min. Ind.
(1)	(2)	(3)	(4)	(5)
Along (Direction parallel to the grain direction of the face veneer)	7 500	6 700	50	45
Across (Direction perpendicular to the grain direction of the face veneer)	4 000	3 600	30	27

(Page 10, clause 10.2.2, third line) — Substitute '7.1.1 to 7.1.6' for '7.1.1 to 7.1.5'.

(Page 10, clause 10) — Insert the following Annex A after clause 10:

ANNEX A **(Clause 5.3)**

METHOD OF TEST FOR EDGE STRAIGHTNESS AND SQUARENESS

C-1 PROCEDURE FOR EDGE STRAIGHTNESS

C-1.1 The straightness of the edges and ends of plywood shall be verified against a straight edge not less than the full length of the plywood. If the edge on the end of the plywood is convex, it shall be held against the straight edge in

Amend No. 2 to IS 709 : 1974

such a way as to give approximately equal gap at each end. The largest gap between the straight edge and the edge shall be measured to the nearest millimetre and recorded.

C-2 PROCEDURE FOR SQUARENESS

C-2.1 The squareness of plywood shall be checked with a 1 200 mm × 1 200 mm square, by applying one arm of the square to the plywood. The maximum width of the gap shall be recorded.

(*Page 11, Appendix A*) — Rename 'Appendix A' as 'Annex B'.

(*Page 12, Appendix B*) — Rename 'Appendix B' as 'Annex C'.

(CED 20)