

AMENDMENT NO. 1 APRIL 2011
TO
IS 742 : 1981 SPECIFICATION FOR ZINC BASE
ALLOY DIE CASTINGS

(Second Revision)

(Page 4, clause 1.1) — Insert '(see Table 1)' at the end.

(Page 5, Table 1) — Substitute the following for the existing:

Table 1 Chemical Composition of Zinc Base Alloy
Die Castings
(Clauses 1.1 and 4.1)

Sl No.	Constituent	Zn Al 4 Percent	Zn Al 4 Cu 1 Percent
(1)	(2)	(3)	(4)
i)	Aluminium	3.8 to 4.2	3.8 to 4.2
ii)	Copper	—	0.7 to 1.1
iii)	Magnesium	0.035 to 0.06	0.035 to 0.06
iv)	Impurities:		
	a) Copper, <i>Max</i>	0.10	—
	b) Iron, <i>Max</i>	0.10	0.1
	c) Lead, <i>Max</i>	0.005	0.005
	d) Cadmium, <i>Max</i>	0.005	0.005
	e) Tin, <i>Max</i>	0.002	0.002
	f) Thallium and Indium, <i>Max</i>	0.001 5	0.001 5
	g) Nickel, <i>Max</i>	0.006	0.006
v)	Zinc	Remainder	Remainder

NOTE — In case of Indium and Thallium, the supplier shall undertake that the material does not contain impurities in limits excess of those laid down above