

AMENDMENT NO. 1 NOVEMBER 1993
TO
IS 8625 : 1986 METHOD FOR DETERMINATION OF
CRUSHING STRENGTH OF IRON ORE PELLETS
(First Revision)

(*Page 4, clause 3*) — Add the following new clause and renumber the subsequent clauses:

‘3. TERMINOLOGY

For the purpose of this standard, the following definition shall apply.

3.1 Crushing Strength

Compressing strength at which an iron ore pellet is broken completely, for which the maximum compressive load attained up to the contraction degree of 50 percent of the initial mean test piece diameter is adopted and which is expressed as the mean value of all measurements of the test sample.’

(*Page 5, clause 5.3*) — Substitute the following for the existing:

‘Record the maximum load where the test piece is compressed up to 50 percent. Contraction of the initial mean test piece diameter to at least one decimal place.’