

AMENDMENT NO. 1 DECEMBER 2018
TO
IS 8737 : 2017 VALVE FITTINGS FOR USE WITH
LIQUEFIED PETROLEUM GAS (LPG) CYLINDERS FOR
MORE THAN 5 LITRE WATER CAPACITY —
SPECIFICATION

(Second Revision)

(Page 2, clause 4.6) — Substitute the following for the existing clause:

4.6 Non-Metallic Materials

4.6.1 Non-metallic materials in contact with LPG shall be compatible with LPG and shall not distort, harden or adhere to the body or seat face to such an extent as to impair the function of the valve.

4.6.1.1 All the rubber components shall comply with the relevant requirement as stipulated in IS 9798 and ozone test as stipulated in IS 3400 (Part 20).

4.6.2 Other than rubber components, that is moulded parts (plastics, etc) shall be subjected to immersion test (resistance to hydrocarbons).

4.6.2.1 Weigh the sample, then immerse it for 72 h into n-pentane, at 20 ± 5 °C. At the end of this period, the sample shall be withdrawn from n-pentane and wiped with absorbent paper. Sample shall be weighed 2 min after its withdrawal from n-pentane. Sample shall again be weighed 24 h after its withdrawal from n-pentane.

4.6.2.2 *Criteria for conformity*

- a) The increase in mass, 2 min after withdrawal from n-pentane, shall be less than 0.3 percent of the initial mass.
- b) The loss in mass, 24 h after withdrawal from n-pentane, shall be less than 0.3 percent of the initial mass.'