

AMENDMENT NO. 1 MAY 1990
TO
IS : 8883 (Part 2/Sec 1) - 1978 METHODS OF
SAMPLING CHEMICALS AND CHEMICAL
PRODUCTS
PART 2 SAMPLING EQUIPMENT

Section 1 For Solids

(*Page 5, clause 3.1.1*) — Insert the following after **3.1.1**:

'3.1.1.1 If required, the following four types of equipments may be used for crushing or grinding the samples to achieve the required particle size:

- a) Lump crushers, such as claw-crushers for breaking lumpy products.
- b) Coarse crushers, such as jaw crushers, impact breakers for primary grinding of coarse products to give 300-100 mm particle size.
- c) Granulating and grinding mills to reduce particle size in the range of 25 mm to less than 1 mm.
- d) Laboratory mills for dealing with relatively small samples and achieving finer grinding, such as jaw crushers (25-2 mm), hammer mills (20 mm - 300 μ m), roll crushers (2 mm - 200 μ m), ball/disc mills (2 mm - 75 μ m). Manual grinding may also be resorted to suitably, such as with a pestle and mortar.'

(CHD 1)