

AMENDMENT NO. 1 AUGUST 2026
TO
IS 8947 : 2021 TEXTILES — MATERIAL (NYLON WEBBING) FOR AIRCRAFT
SAFETY BELTS — SPECIFICATION
(First Revision)

(Page 1, clause 3.1) — Substitute the following for the existing:

‘The nylon yarn used for the manufacture of nylon webbing shall be nylon 6 or nylon 6,6 of high tenacity, having a minimum tenacity of 0.7 N/tex (8 gf/d). The linear density of the yarn shall be 93 tex (840 denier) with a tolerance of ± 10 percent. The yarn shall have a minimum twist of 100 turns per metre (TPM) when determined in accordance with IS 832 (Part 1).’

[Page 1, Table 1, Sl No. (ii)] — Substitute the following for the existing:

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
ii)	Width, mm	50.0 ± 1.5	IS 1954