

AMENDMENT NO. 2 APRIL 2005
TO
IS 5915 : 1970 SPECIFICATION FOR SINGLE
TEXTURE RUBBERIZED WATERPROOF FABRICS

[Page 7, Table 1, Sl No. (iii)] — Substitute the following for the existing:

Sl No.	Characteristic	Type 1				Type 2				Method of Test, Ref to
		Quality 1		Quality 2		Quality 1		Quality 2		IS No.
		Grade A	Grade B	Grade A	Grade B	Grade A	Grade B	Grade A	Grade B	
iii)	Breaking strength N/5 cm grip, Min: a) Warp b) Weft	400 350	400 350	400 350	400 350	400 350	400 350	400 350	400 350	7016 (Part 2) : 1981*
*Methods of test for coated and treated fabrics : Part 2 Determination of breaking strength and extension at break (first revision).										

(PCD 13)

Reprography Unit, BIS, New Delhi, India