

AMENDMENT NO. 1 OCTOBER 1978

TO

IS : 6058-1970 SPECIFICATION FOR RUBBER COMPONENTS FOR TRANSFUSION FLUID BOTTLES

Alterations

(Pages 3 and 4, clause 0.5) — Substitute the following for the existing clause:

'0.5 At present, most of the rubber laboratories in this country have no facilities for carrying out tests for toxicity and for detecting inhibitory substances in the rubber components. However, where facilities are available, methods given in Appendices B and C may be followed.'

(Page 9, clauses 6.4 and 6.4.1) — Substitute the following for the existing clauses:

'6.4 Test for Metallic Contamination in Components

6.4.1 Preparation of Test Solution

6.4.1.1 Tubing — Pass 40-ml portions of sterile pyrogen-free isotonic saline solution containing 9 g of sodium chloride per litre at room temperature through a metre-length tubing at a flow rate of approximately 10 ml per minute and collect the effluent. Make up the solution to 250 ml.

6.4.1.2 Bungs and discs — Immerse 5 g of the sample cut to small pieces in 25 ml of sterile pyrogen-free isotonic saline solution containing 9 g of the sodium chloride per litre at room temperature for about 5 minutes. Collect the solution in a suitable container and make up the solution to 250 ml.'

(Page 10, Appendix B) — Substitute the following for the existing appendix:

'A P P E N D I X B

(Clause 0.5)

TEST FOR TOXICITY

B-1. PREPARATION OF EXTRACT

B-1.1 Tubing — Fill specimens of tubing, each 150 mm in length, as completely as practicable with sterile pyrogen-free isotonic saline solution containing 9 g of sodium chloride per litre. Clamp the ends

securely to retain the solution and immerse the filled set completely in water. Heat the water and maintain it at 85°C for 1 hour. Collect the contents of the tubings in a suitable container and cool to room temperature.

B-1.2 Bungs and Discs — Immerse 1 g of the sample cut to small pieces (each approximately 3 mm cube in size) in 5 ml of sterile pyrogen-free isotonic saline solution containing 9 g of sodium chloride per litre, in a test tube. Close the test tube with a suitable stopper and immerse the same in water with the closed end above the surface of water. Heat the water and maintain it at not less than 85°C for 1 hour. Collect the solution in a suitable container and cool to room temperature.

B-2. PROCEDURE

B-2.1 Inject intravenously the solution prepared as described in **B-1**, into each of five healthy mice weighing 20 ± 3 g each. At the end of 4, 24 and 48 hours examine the animals for discernible symptoms of toxicity. If any of the animals show gross signs of toxicity or die, repeat the test with five unused mice weighing 20 ± 3 g each.

B-2.2 The test shall be deemed to be satisfied if all the animals survive for 48 hours.'

(Pages 10 and 11, clause **C-1.1**, lines 4 to 6) — Substitute 'Cut 5 mm long strips of convenient width and thickness from the sample of rubber component. Wash the strips in distilled water, then sterilize them by autoclaving in distilled water for 30 minutes at 120°C' for 'Select 5-mm length of representative sample of the tubing. Wash the tubing sample in distilled water, then sterilize them by autoclaving in distilled water for 30 minutes at 120°C.'

Addendum

(Page 6, clause **3.2.7.3**) — Add the following new clauses after **3.2.7.3**:

3.2.8 The components shall be free from harmful contamination of heavy metals, namely, arsenic, copper, iron and manganese.

3.2.8.1 The concentration of each of the metallic impurities in **3.2.8** shall not exceed 5 ppm in sterile pyrogen-free isotonic saline solution prescribed in **6.4**.'