

AMENDMENT NO. 1 JUNE 1999
TO
IS 6158 : 1984 RECOMMENDED PRACTICE FOR
SAFEGUARDING AGAINST EMBRITTLEMENT OF
HOT-DIP GALVANIZED IRON AND STEEL PRODUCTS
(Second Revision)

(Page 4, clause 1.1) — Substitute the following for the existing clause:

'1.1 This standard prescribes factors which are responsible for causing embrittlement in steel products during galvanizing process and procedure for detecting embrittlement and to safeguard against them.'

(Page 4, clause 2) — Insert the following new clauses and renumber the subsequent clauses:

'2 TERMINOLOGY

2.1 Embrittlement — It is the total or partial loss of ductility in steel. An embrittled product characteristically fails by fracture without appreciable deformation. Types of embrittlement usually encountered in galvanized steel are related to ageing phenomena, cold working and absorption of hydrogen.'

[Page 4, clause 2.1 (renumbered 3.1)] — Substitute the following for the existing Clause:

'2.1 Base Metal(Steels) — Only steels produced by open hearth, basic oxygen and electric furnace shall be used for galvanizing. Basic open-hearth or basic electric steel should always be specified with carbon and phosphorus content being as low as practicable. Bessemer steels should never be used where the material is cold formed and not subsequently annealed prior to galvanizing. Carbon should not exceed 0.25 percent where severe cold-forming operations precede galvanising.'

[Page 5, clause 2.2.3 (renumbered 3.2.3)] — Substitute the following for the existing clause:

'2.2.3 The smaller hot rolled shapes including thicknesses up to 6 mm , may be cold worked by punching without subsequent annealing or stress relieving. Shapes 8 mm to 17 mm in thickness are not seriously affected as to serviceability

Amend No. 1 to IS 6158 : 1984

by cold working in punching. The heavier shapes, 18 mm and over, should be reamed or drilled after punching or suitably thermally treated prior to galvanising.'

[Page 6, clause 3.2.2.1 (renumbered 4.2.2.1)] — Substitute '25 mm' for '2.5 mm'.

(MTD 20)