

AMENDMENT NO. 2 JUNE 1978
TO
IS : 6179-1971 SPECIFICATION AND SAFETY
REQUIREMENTS FOR RIGID SIDED PLAYPENS

Alteration

(Page 4, clauses **3.1.4** and **3.1.4.1** (see also Amendment No. 1)] —
 Substitute the following for the existing clauses:

- 3.1.4** Two coats of enamel paint shall then be applied as follows:
- a) Undercoat conforming to IS:149-1950||, IS:2932-1975¶ or IS:2933-1975**, and
 - b) Finish coat with enamels conforming to IS:151-1950‡, IS:2932-1975¶ or IS:2933-1975**.

3.1.4.1 In the case of stoving enamel the components shall thereafter be baked at a specified temperature in an oven heated uniformly. The finish shall be smooth and uniform with a hard and tough film of enamel strongly adhering to the surface. The finish shall be free from all visible defects and the film shall not chip when tapped lightly with a dull pointed instrument.'

Addendum

[Page 4, foot-notes (see also Amendment No. 1)] — Add the following new foot-notes:

' ||Specification for ready mixed paint, spraying, undercoating, stoving, for enamels and general purposes, colour as required.

¶Specification for enamel, synthetic, exterior, (a) undercoating, (b) finishing (*first revision*).

**Specification for enamel, exterior, (a) undercoating, (b) finishing (*first revision*). '