

AMENDMENT NO. 3 MAY 1980
TO
IS : 6179 - 1971 SPECIFICATION AND SAFETY
REQUIREMENTS FOR RIGID SIDED PLAYPENS

Alterations

(*Page 4, clauses 3.1.1 and 3.1.2*) — Substitute the following for the existing clauses:

“3.1.1 All dents, burrs and sharp edges shall be removed from various components. The components shall be individually pickled, scrubbed and rinsed to remove grease, rust, scale or any other foreign element.

3.1.2 Immediately after pickling, all the mild steel parts shall be given phosphating treatment conforming to Class C of IS : 3618-1966*. The process for application of phosphate coating shall be in accordance with IS : 6005-1970 ‘Code of practice for phosphating of iron and steel’.”

[*Page 4, clause 3.1.4 (see Amendments No. 1 and 2)*] — Substitute the following for the existing clause:

‘3.1.4 Coat/coats of enamel paint shall then be applied as follows:

Finish coat with enamels conforming to IS : 151-1950†, IS : 2932-1974¶ or IS : 2933-1975**.’

Addendum

(*Page 6, clause 5.1*) — Add the following new clauses after 5.1 and renumber the subsequent clauses accordingly:

“6. PERFORMANCE REQUIREMENTS OF FINISH

6.1 Scratch Hardness Test — A sample of mild steel plate 150 × 50 mm in size and thickness 0.315 mm finished as described in 3 shall be subjected to scratch hardness test in accordance with 15.1 of IS : 101-1964 ‘Methods of test for ready mixed paints and enamels (*second revision*)’. A scratch, showing the bare metal shall not be produced on the test sample.

6.2 Pressure Test — Samples prepared from mild steel plates of thickness 0.315 mm and finished as described in 3 shall be subjected to pressure test in accordance with 15.2 of IS : 101-1964. The metal surface shall not be rendered visible when the test pieces are separated after the test.

6.3 Flexibility and Adhesion on Test — A sample of mild steel plate 150×50 mm in size and thickness 0.315 mm finished as described in **3** shall be subjected to flexibility and adhesion test in accordance with **16** of IS : 101-1964. The paint film on the test piece shall not show damage, detachment or cracking when examined under $\times 10$ magnification.

6.4 Stripping Test — A sample of mild steel plate 150×50 mm in size and thickness 0.315 mm and finished as described in **3** shall be subjected to stripping test in accordance with **17** of IS : 101-1964. The scratch produced after the test shall be free from jagged edges.

6.5 Test for Protection Against Corrosion under Conditions of Condensation — A mild steel panel of size 150×100 mm and thickness 1.25 mm finished as described in **3** shall be subjected to test for protection against corrosion under conditions of condensation in accordance with **18** of IS : 101-1964. The metal surface shall show no signs of corrosion after the test."

(BDC 35)