

AMENDMENT NO. 2 MAY 2009
TO
IS 6198 : 1992 LEDGED, BRACED AND BATTENED
TIMBER DOOR SHUTTERS — SPECIFICATION

(Second Revision)

(Page 4, clause 9) — Substitute the following for the existing:

9 TESTS

Door shutters shall be subjected to the following tests.

9.1 Dimensions and Squareness Test

When tested in accordance with IS 4020 (Part 2), the dimensions of nominal width and height of door shutters shall be within a limit of ± 3 mm. The door shutter shall not deviate by more than 1 mm on a length of 500 mm. The thickness of the door shutter shall be uniform throughout, with the permissible variation of not more than 0.8 mm between any two points. The nominal thickness of the shutter shall be within a limit of ± 1 mm.

9.2 General Flatness Test

When tested in accordance with IS 4020 (Part 3), the twist, cupping and warping of door shutters shall not exceed 6 mm.

9.3 Local Planeness Test

When tested in accordance with IS 4020 (Part 4), the depth of deviation measured at any point on door shutters shall not be more than 0.5 mm.

9.4 Flexure Test

When tested in accordance with IS 4020 (Part 6), there shall not be any residual deflection of more than one-tenth of the maximum deflection in the door shutters. The deflection at the maximum load shall not be more than one-thirtieth of the length of the door shutter and one fifteenth of the width of the door shutter, whichever is less.

9.5 Edge Loading Test

When tested in accordance with IS 4020 (Part 7), the deflection of the edge of door shutters at the maximum load shall not be more than 5 mm. On removal of the loads, the residual deflection shall not be more than 0.5 mm, failing which the test may be repeated on the other edge in the reverse direction. Also there shall be no lateral buckling by more than 2 mm during loaded condition and no residual lateral buckling after removal of the load.

9.6 Shock Resistance Test

9.6.1 When tested for soft and light body impact test in accordance with IS 4020 (Part 8), there shall be no visible damage in any part of the door shutter after twentyfive blows on each end.

9.6.2 When tested for soft and heavy body impact test in accordance with IS 4020 (Part 8), the normally hung door shutter, with hangings, fixings and fastenings should withstand without any significant permanent deformation and without deterioration the five impacts on both sides of the shutter.

9.7 Buckling Test

Door shutters, when tested in accordance with IS 4020 (Part 9), shall not show any deterioration and any residual deformation of more than 5 mm after 15 min of unloading. The initial deflection also shall not be more than 50 mm.

9.8 Slamming Test

9.8.1 Any one of the following tests given in **9.8.2** and **9.8.3** shall be used.

9.8.2 Door shutters, when tested in accordance with **2** of IS 4020 (Part 10), shall not have any visible damage in any part of the door at the end of 50 successive impacts.

9.8.3 Door shutters, when tested in accordance with **3** of IS 4020 (Part 10), shall not have any visible damage in any part of the door at the end of 100 successive impacts.

9.9 Misuse Test

When tested in accordance with IS 4020 (Part 11), there shall not be any permanent deformation of the fixing or any other part of the doorset, hindering its normal working after the test.

9.10 Screw Withdrawal Resistance Test

When tested in accordance with IS 4020 (Part 16), the required load to withdraw the screw completely from the door shutter shall be more than 1 000 N. On withdrawal, there shall be no visible damage to the surface either by delamination or extra-chipping off at the points of withdrawal.

[Page 4, clause **11** (*see also Amendment No. 1*)] — Insert ‘**ADDITIONAL**’ before the existing title.

(Page 5, Annex B) — Insert the following as appropriate and delete ‘13034 : 1990 Methods of tests for timber panelled and glazed door shutters — Type tests’:

‘4020 (Parts 1 to 16) : 1998 Door shutters — Methods of tests (*third revision*)’

