

AMENDMENT NO. 4 AUGUST 2023
TO
IS 17261 : 2022 TEXTILES — POLYESTER CONTINUOUS FILAMENT FULLY
DRAWN YARNS — SPECIFICATION
(First Revision)

[Page 4, clause 5.2.1 (a)] — Substitute the existing for the following:

‘Microscopic and dissolution test given in IS 667 and melting point of 240 °C, *Min* when tested as per method specified in Annex H of IS 16481. The melting point for low melt polyester shall be 110 °C, *Min*; or’

[Page 6, Table 3, Sl No. viii), col (3)] — Substitute ‘100 – 600 (111 – 667)’ for ‘120 – 450 (133 – 500)’

[Page 6, Table 3, Sl No. ix), col (3)] — Substitute ‘10 – 100 (11 – 111)’ for ‘10 – 40 (11 – 44.5)’

(Page 6, Table 3, Note 2) — Substitute the following for existing:

‘Interlace in nips per meter shall be 5 to 35 with a tolerance of ± 5 subject to a minimum of 5 when tested by the method prescribed in Annex B of IS 17262, except for mother yarns and mono yarns, where interlace can be up to zero.’

(Page 7, Table 4) — Insert the following note 2 after the existing note and renumber the existing note as note 1:

‘2 The requirement for Isophthalic acid (IPA) content shall not be applicable for low melt polyester fully drawn yarn.’

(Page 8, clause 7.1, sentence 1) — Substitute ‘15’ for ‘11’