

AMENDMENT NO. 7 JULY 2025
TO
IS 17261 : 2022 TEXTILES —POLYESTER CONTINUOUS FILAMENT FULLY
DRAWN YARNS — SPECIFICATION
(First Revision)

(Page 1, clause 1.1) — Substitute the following for existing:

‘1.1 This standard specifies requirements for all types of virgin and recycled polyester continuous single multifilament or monofilament flat fully drawn yarns (FDY) for various end usages. It also covers the requirements for single multifilament twisted fully drawn yarns (FDY) for various end uses.’

[Page 1, clause 3.13 (see also Amendment No. 3)] — Insert the following at the end:

‘3.14 Polyester Twisted Filament Yarn — Polyester twisted filament yarns are those yarns that have been formed by imparting the twist in S or Z direction.’

[Page 4, clause 5.2.1(a), (see also Amendment No. 4)] — Substitute the existing for the following:

- a) Microscopic and dissolution test given in IS 667 and melting point of 240 °C, *Min* when tested as per method specified in Annex H of IS 16481. The melting point for low melt polyester shall be 125 °C, *Max*; or’.

(Page 6, Table 3, Note) — Insert the following at the end:

‘4 For polyester twisted yarns, the twist shall be declared by the manufacturer subject to the tolerance of ± 5 % on the declared value when tested as per the method prescribed in IS 832 (Part 1).’

(Page 11, Annex A) — Insert the following entry at appropriate place:

<i>‘IS No.</i>	<i>Title</i>
IS 832 (Part 1) : 2021/ISO 2061 : 2015	Textiles — Determination of twist in yarns: Part 1 Direct counting method (<i>third revision</i>)’.