

## AMENDMENT NO. 2 FEBRUARY 2023

### TO

## IS 17262 : 2022 TEXTILES — POLYESTER PARTIALLY ORIENTED YARN (POY) — SPECIFICATION

( *First Revision* )

(Page 1, Clause 3.2) — Substitute the following for existing.

**‘3.2 Commercial Allowance** — A defined percentage to be added to the net mass of the yarns at ambient conditions for the calculation of commercial mass and certain other properties.

NOTE — The commercial allowance for polyester POY shall be 2.0 percent.’

(Page 1, Clause 3.3) — Substitute the following for existing.

**‘3.3 Commercial Mass** — The mass obtained by adding to the net mass at ambient conditions, the mass corresponding to the commercial allowance.’

(Page 1, Clause 3.9) — Substitute the following for existing:

### **‘3.9 Mass**

#### **3.9.1 Gross Mass**

The total mass of a consignment, or of any part of a consignment, including the yarn and the tare.

#### **3.9.2 Net Mass**

The difference between the gross mass and the corresponding tare, determined at the same time.

#### **3.9.3 Tare**

The sum of the masses of all the packing materials such as pallets, wrappers and covers, tie bands/straps, paper tubes, etc., relating to a consignment or to any part of a consignment.’

(Page 3, Clause 4.4.3) — Substitute ‘Bright (BRT)/Optically White (OW)’ for ‘Bright (BRT)/Optically Bright (OBRT)’.

(Page 3, Clause 4.5.3) — Substitute ‘Dope Dyed (DD)’ for ‘Dope Dyed (DD)/Optically White (OW)’.

(Page 4, Table 2) — Insert the followings rows after Sl No. xii):

|                    |        |
|--------------------|--------|
| ‘xiii) Virgin yarn | VFDY   |
| xiv) Recycled yarn | RFDY’. |

[Page 4, Table 2, Sl No. (vii), col (3)] — Substitute ‘Optically White (OW)’ for ‘Optically Bright (OBRT)’.

[Page 6, Table 5, Sl No. (iii), col (2)] — Substitute ‘Bright (BRT)/Optically White (OW)’ for ‘Bright (BRT)/OBRT’.

(Page 6, Clause 6.5) — Insert the following after sentence 1:

‘The requirements of color fastness to rubbing and color fastness to perspiration (acidic and alkaline) shall be optional.’

**Price Group 2**

**Amendment No. 2 to IS 17262 : 2022**

(Page 6, Clause 6.6, see Amendment 1) — Substitute the following for existing:

**‘6.6 Commercial Mass**

The commercial mass shall be obtained by adding mass corresponding to commercial allowance of 2.0 percent to the net mass of the consignment at ambient conditions and it shall not be less than the declared commercial mass of the consignment.’

[Page 7, Table 6, Sl No. (iii), col (2)] — Substitute ‘Rubbing (optional)’ for ‘Rubbing’.

[Page 7, Table 6, Sl No. (iv), col (2)] — Substitute ‘perspiration (acidic and alkaline) (optional)’ for ‘perspiration (acidic and alkaline)’.

[Page 8, Clause 8.1 (c)] — Substitute ‘Gross or net mass of each carton/pallet;’ for ‘Commercial mass of each carton/pallet’.

(Page 9, Annex A) — Delete the following reference:

‘IS 7703 (Part 3) : 1991 Methods of test for continuous filament polyester and polyamide flat yarn — Commercial mass (first revision)’.

(Page 10, Annex B-1.3) — Insert the following note under the clause:

‘NOTE — Conditioning of samples for at least 4 h is sufficient to attain moisture equilibrium.’

(Page 10, Annex B-0, line 2) — Substitute ‘three’ for ‘two’.

(Page 11, Annex B) — Insert the following after B-2.4:

**‘B-3 DETERMINATION OF INTERLACE OF FILAMENT YARN IN NIPS PER METRE BY WATER BATH METHOD**

**B-3.1 PRINCIPLE**

In this method, the yarn is placed in a water bath containing clean water and the number of interlacing are counted visually. This method is applicable for testing of nips per metre of POY and FDY Yarn.

**B-3.2 Apparatus**

**B-3.2.1** Water bath with hooks at both ends for tying the yarn.

**B-3.2.2** One metre stainless steel scale with 1 mm least count.

**B-3.3 PROCEDURE**

**B-3.3.1** The water bath shall be filled with clean water up to the outlet nozzle or marker.

**B-3.3.2** Constant level of water shall be maintained in water bath.

**B-3.3.3** Take the yarn sample and tie one end of the sample at the hook on the water bath and just stretch the yarn and put the yarn in a water bath and tie the other end of yarn sample to the hook on the other side.

**B-3.3.4** The yarn will start floating on the water surface.

**B-3.3.5** Visually count the no of interlace points in one metre length and record it.

**B-3.3.6** Four samples from each package and a total of 20 samples shall be tested. Average of all the 20 readings shall be reported.

(Page 11, *Annex C-3*) — Insert the following note under the clause:

‘NOTE — Conditioning of samples for at least 4 h is sufficient to attain moisture equilibrium.’